<u>SPECIFICATION</u>

HIGH VALUE MULTILAYER CERAMIC CAPACITORS

212 T	YPE (X	5R, X7R	, Y5V, Y	75U, X5	S, X6S)			
 (Equiv	valent	to EIA:	CC080)5)		 	 	

Document No.

Specifications Date: 30.NOV.2009 Multilayer Ceramic Chip Capacitor NICKEL BASED ELECTRODES

MLCEE10003

Item

Multilayer Ceramic Capacitor Class II (CC0805)

1. Scope

This specification covers multilayer chip type ceramic capacitor (Pb-Free) for use in electronic appliances and electric communication equipment.

2. Part Numbering System

Part number is indicated as follows:

(Example) Ni based electrodes: U MK 212 BJ 104 K G $\overline{}$ $\overline{}$

① Rated voltage

	_
Code	Voltage
J	6.3V
L	10V
E	16V
Т	25V
G	35V
U	50V

② Size (mm)

_	,
Code	Size
212	2.0×1.25

4 Tolerance

Code	Tolerance
K	±10%
М	±20%
Z	+80,-20%

⑥ Packaging

Packaging	Code
Taping	-T/-TD

③ Temperature Characteristic

Class II	Capacitance change rate	Temperature range	Reference temperature
BJ (X5R)	±15%(EIA)	-55∼+85°C	25 ℃
B7 (X7R)	±15%(EIA)	-55∼+125℃	"
F (Y5V)	+22%-82%(EIA)	-30∼+85℃	25 ℃

⑤ Thickness code (Ni based electrodes)

Туре	Thickness rank (mm)	Code
	0.45	K
212	0.85	D
	1.25	G

Multilayer Ceramic Chip Capacitor

3. Test Conditions

Standard test conditions shall be temperature of 5 to 35°C, relative humidity of 45 to 85% and air pressure of 86 to 106kPa. Test shall be conducted at temperature of 25±3°C, relative humidity of 60 to 70% and air pressure of 86 to 106kPa if test result is suspectable.

Unless otherwise specified, all tests shall be conducted under standard test conditions.

4. Construction, Dimensions and Performance

Details of construction, dimensions and performance shall be specified in the following pages.

5. Packaging

Packaging shall be made to avoid damages of capacitors during transportation or storage. And it shall be marked with part number, quantity, lot number and manufacturer's name on its appropriate position.

6. Manufacturing site

TAIYO YUDEN CO., LTD. (JAPAN)
TAIYO YUDEN (SARAWAK) SDN, BHD. (MALAYSIA)
KOREA KYONG NAM TAIYO YUDEN CO., LTD. (KOREA)
TAIYO YUDEN (GUANG DONG) CO., LTD. (CHINA)
TAIYO YUDEN (PHILIPPINES) INC. (PHILIPPINES)

7. Precautions

- Please refer to precautions in our general catalog prior to product usage.

 If you need further information, please contact us.
- ·CAUTION: Contents of this specification cannot be assured with Sn-Zn lead-free solder usage.

8. Storage conditions

- To maintain the solderability of terminal electrodes and to keep the packaging material in good condition, care must be taken to control temperature and humidity in the storage area. Humidity should especially be kept as low as possible.
- Recommended conditions

Ambient temperature: 30°C and below Humidity: 70% RH and below

The ambient temperature must be kept below 40° C. Even under ideal storage conditions, capacitor electrode solderability decreases with time. Therefore ceramic chip capacitors should be used within 6 months from the time of delivery. If exceeding the above period, please check solderability before using the capacitors.

• The packaging material should be kept where no chlorine or sulfur exists in the air.

Multilayer Ceramic Chip Capacitor
 9. RoHS compliance • This product conform to RoHS. • "RoHS compliance" means that the product does not contain lead, cadmium, mercury, hexavalent chromium, PBB or PBDE referring to EU Directive 2002/95/EC, except other non-restricted substances or impurities which cannot be technically removed at refining process.

No.	Item	Specified Value	Remarks
1	Operating Temperature Range	Capable of continuous operation under these conditions.	BJ(X5R) : -55∼+85°C B7(X7R) : -55∼+125°C F(Y5V) : -30∼+85°C
2	Shape and Dimensions	Per Fig.1	
3	Heat Treatment		Initial value shall be measured after test sample is heat-treated at 150 +0/-10°C for an hour and kept at room temperature for 24±2hours.
4	Voltage Treatment		Initial value shall be measured after test sample is voltage-treated for an hour at temperature and voltage which are specified as test conditions, and kept at room temperature for 24 ± 2 hours.
5	Dielectric Withstanding Voltage (between terminals)	No abnormality	Conforming to EIA RS-198-D (1991). 250% of DC rated voltage shall be applied for 1 to 5 seconds. Charging and discharging current shall be 50mA or less.
6	Insulation Resistance	Per Table1	Conforming to EIA RS-198-D (1991). Voltage for the measurement shall be rated voltage and voltage applying time shall be 1 minute \pm 5 seconds. Charging and discharging current shall be 50mA or less.
7	Capacitance and Tolerance	Per Table1	Conforming to EIA RS-198-D (1991). Heat treatment specified in No.3 of the specification shall be conducted prior to measurement. Measuring frequency and voltage shall conform to the table shown below. No. Measuring Measuring Voltage 1 120Hz±10Hz 0.5±0.1Vrms 2 1kHz±10% 1.0±0.2Vrms 3 1kHz±10% 0.5±0.1Vrms
8	Dissipation Factor (DF)	Per Table1	Conforming to EIA RS-198-D (1991). Heat treatment specified in No.3 of the specification shall be conducted prior to measurement. Measuring frequency and voltage shall conform to the table shown below. No. Measuring Measuring Voltage 1 120Hz±10Hz 0.5±0.1Vrms 2 1kHz±10% 1.0±0.2Vrms 3 1kHz±10% 0.5±0.1Vrms

No.	Item	Specified Value	Remarks
9	Temperature Characteristic	Per P1③Temperature Characteristic	Conforming to EIA RS-198-D (1991). Heat treatment specified in No.3 of the specification shall be conducted prior to measurement. Maximum capacitance deviation in both (+) and (-) sides in range of lowest temperature to highest temperature for capacitor shall be indicated in ratio of variation in reference to capacitance value at reference temperature.
10	Adhesive Force of Terminal Electrodes	Terminal electrodes shall be no exfoliation or a sign of exfoliation.	Test sample shall be soldered to test board shown in Fig.2 and a force of 5N{0.51kgf} shall be applied in arrow direction for 30 ± 5 seconds.
11	Vibration	Initial performance shall be satisfied.	Conforming to EIA RS-198-D (1991). Test sample shall be soldered to board shown in Fig.2. Heat treatment specified in No.3 of the specification shall be conducted prior to test. Test conditions: Frequency range: 10~55Hz Overall amplitude: 1.5mm Sweeping method: 10~55~10Hz for 1 min. Each two hours in X,Y,Z direction: 6 hours in total

No.	Item		Specified Value	Remarks		
12	Resistance to Soldering Heat	Appearance Capacitance Change Dissipation Factor Insulation Resistance Dielectric Withstanding Voltage (between terminals)	No abnormality Per Table2 Per Table2 Initial value shall be satisfied. No abnormality	Conforming to EIA RS-198-D (1991). Test sample shall be completely submerged in molten solder of $270\pm5^{\circ}\mathbb{C}$ for 3 ± 0.5 seconds. Preheating as shown in the table below shall be continuously conducted before submersion and test sample shall be kept at normal temperature after test.		
13	Solderability		More than 95% of terminal electrode shall be covered with fresh solder.	 【Eutectic】 Used solder shall be [JIS Z 3282 H60A or H63A]. Test sample shall be completely submerged in molten solder of 230±5°C for 4±1 seconds. 【Pb free】 Used solder shall be [Sn/3.0Ag/0.5Cu]. Test sample shall be completely submerged in molten solder of 245±3°C for 4±1 seconds. 		
14	Shock Capacitance Per Tab Change Dissipation Factor Per Tab		No abnormality Per Table2 Per Table2 Initial value shall be	Conforming to EIA RS-198-D (1991). Test sample shall be soldered to board shown in Fig.2. Heat treatment specified in No.3 of the specification shall be conducted prior to test. Test sample shall be kept for specified time at each of temperature in steps 1 to 4 shown below in sequence.		
		Resistance Dielectric Withstanding Voltage (between terminals)	satisfied. No abnormality			

No.	Item		Specified Value	Remarks
15	Humidity (Steady	Appearance	No abnormality	Conforming to EIA RS-198-D (1991). Test sample shall be at 40 ± 2 °C with relative
	State)	Capacitance Change	Per Table2	humidity of 90 to 95% for 500 +24/-0 hours. Heat treatment specified in No.3 of the specification
		Dissipation Factor	Per Table2	shall be conducted prior to test. Measurement shall be conducted after test sample is
		Insulation Resistance	Per Table2	kept for 24±2 hours.
16	High Temperature	Appearance	No abnormality	Conforming to EIA RS-198-D (1991). Test sample shall be put in thermostatic oven with
	Loading	Capacitance Change	Per Table2	maximum temperature and DC voltage shall be continuously applied for 1000 +48/-0 hours
		Dissipation Factor	Per Table2	Applied DC voltage is described in table2. Charging and discharging current shall be 50mA or
Insulation Resistance Per Table2 less. Voltage specificat Measurer	less. Voltage treatment specified in No.4 of the specification shall be conducted prior to test. Measurement shall be conducted after test sample is kept for 24 ± 2 hours.			
17	Humidity Loading	Appearance	No abnormality	Conforming to EIA RS-198-D (1991). Test sample shall be put in thermostatic oven with 40
		Capacitance Change	Per Table2	$\pm 2^{\circ}$ C and relative humidity 90 to 95% and DC rated voltage shall be continuously applied for 500 +24/-0
		Dissipation Factor	Per Table2	hours. Charging and discharging current shall be 50mA or
		Insulation Resistance	Per Table2	less. Voltage treatment specified in No.4 of the specification shall be conducted prior to test. Measurement shall be conducted after test sample is kept for 24 ± 2 hours.
	Test sample shall be soldered to test board as shown in Fig.3.			
		Capacitance Change	BJ/B7: ±12.5% F: ±30%	Soldering shall be conducted with care of avoiding an abnormality such as heat shock. Deflection test is such that force to cause deflection as much as 1.0mm is applied for 10 seconds in method shown in Fig.4. Measurement shall be conducted with deflection of 1.0mm.

Table 1 Nominal Capacitance Range and Tolerance

	Temperat ure	Capacit ance	Insulation Resistance(DF(%m ax.)	Measuri ng a		Thickness	(mm) ※4	Solderin	ng method
Ordering code 1:41	characteri stics	(μF)	$M \ \Omega + \mu$		conditio	L:%4	W <u>%4</u>	t	Wave	Reflow
	(JIS/EIA)		F)min※2		11/2/3					
UMK212 BJ104□G	B/X5R	0.10		3.5	2	M	М	1.25±0.1	0	0
UMK212 BJ224□G	B/X5R	0.22		3.5	2	М	М	1.25±0.1	0	0
UMK212 BJ474□G	B/X5R	0.47		3.5	2	М	М	1.25±0.1	0	0
UMK212 BJ105□G	B/X5R	1.0		5.0	2	М	М	1.25±0.1	0	0
TMK212 BJ474□D	B/X5R	0.47	100	3.5	2	М	М	0.85±0.1	×	0
TMK212 BJ105□D	B/X5R	1.0	100	5.0	2	М	М	0.85±0.1	×	0
TMK212 BJ225□D	B/X5R	2.2	100	5.0	2	Q	Q	0.85±0.1	×	0
TMK212 BJ475□D-TD	X5R	4.7		10.0	2	R	R	0.85±0.1	×	0
TMK212 BJ225□G	B/X5R	2.2	100	5.0	2	М	М	1.25±0.1	×	0
TMK212 BJ475□G	X5R	4.7	100	10.0	2	Q	Q	1.25±0.15	×	0
EMK212 BJ105□D	B/X5R	1.0	100	5.0	2	М	М	$0.85\!\pm\!0.1$	×	0
EMK212 BJ225□D	B/X5R	2.2	100	5.0	2	Q	Q	0.85±0.1	×	0
EMK212 BJ475□D	B/X5R	4.7		10.0	2	М	М	0.85±0.1	×	0
EMK212 BJ106□D-TD	X5R	10.0	100	10.0	2	Q	Q	0.85±0.1	×	0
EMK212 BJ225□G	B/X5R	2.2		5.0	2	М	М	1.25±0.1	×	0
EMK212 BJ475□G	B/X5R	4.7	100	5.0	2	Q	Q	1.25±0.15	×	0
EMK212 BJ106□G	X5R	10.0	100	10.0	2	Q	Q	1.25±0.15	×	0
LMK212 BJ475□K	X5R	4.7	100	10.0	2	Q	Q	$0.45\!\pm\!0.05$	×	0
LMK212 BJ105□D	B/X5R	1.0		3.5	2	М	М	0.85±0.1	×	0
LMK212 BJ225□D	B/X5R	2.2	100	5.0	2	М	М	0.85±0.1	×	0
LMK212 BJ475□D	B/X5R	4.7		10.0	2	М	М	0.85±0.1	×	0
LMK212 BJ106□D	X5R	10.0	100	10.0	2	Q	Q	$0.85\!\pm\!0.1$	×	0
LMK212 BJ225□G	B/X5R	2.2		5.0	2	М	M	1.25±0.1	×	0
LMK212 BJ475□G	B/X5R	4.7	100	5.0	2	Q	Q	1.25±0.15	×	0
LMK212 BJ106□G	X5R	10.0	100	10.0	2	Q	Q	1.25±0.15	×	0
LMK212 BJ226MG	X5R	22.0	100	10.0	1	R	R	1.25±0.2	×	0
JMK212 BJ475□K	X5R	4.7	100	10.0	2	Q	Q	0.45 ± 0.05	×	0
JMK212 BJ106MK	X5R	10.0	100	10.0	3	Q	Q	0.45 ± 0.05	×	0
JMK212 BJ475□D	X5R	4.7		10.0	2	М	М	0.85±0.1	×	0
JMK212 BJ106□D	X5R	10.0	100	10.0	2	Q	Q	0.85±0.1	×	0
JMK212 BJ226MD	X5R	22.0	100	10.0	1	Q	Q	0.85±0.1	×	0
JMK212 BJ475□G	B/X5R	4.7	100	5.0	2	Q	Q	1.25±0.15	×	0
JMK212 BJ106□G	X5R	10.0	100	10.0	2	Q	Q	1.25±0.15	×	0
JMK212 BJ226MG	X5R	22.0	100	10.0	1	Q	Q	1.25±0.15	×	0
JMK212 BJ476MG	X5R	47.0	100	10.0	1	R	R	1.25±0.2	×	0
UMK212 F224ZD	F/Y5V	0.22		7.0	2	М	M	0.85±0.1	0	0
UMK212 F474ZG	F/Y5V	0.47		7.0	2	M	M	1.25±0.1	0	0
UMK212 F105ZG	F/Y5V	1.0		7.0	2	М	М	1.25±0.1	0	0
EMK212 F225ZG	F/Y5V	2.2		7.0	2	М	М	1.25±0.1	0	0
LMK212 F225ZD	F/Y5V	2.2		9.0	2	М	М	0.85±0.1	×	0
LMK212 F475ZG	F/Y5V	4.7		9.0	2	М	M	1.25±0.1	×	0
LMK212 F106ZG	F/Y5V	10.0		16.0	2	М	M	1.25±0.1	×	0
JMK212 F475ZD	F/Y5V	4.7		16.0	2	М	М	0.85±0.1	×	0
JMK212 F106ZG	F/Y5V	10.0		16.0	2	М	M	1.25±0.1	×	0

[Note] $\%1:\square$ is for Tolerance code K or M.

 $\mbox{\%2}$: Blank indicates 500M Ω • μ F min.

%3 : Per P4%4 : Per Table3

Table 1 Nominal Capacitance Range and Tolerance

Ordering code※1	Tempera ture character	Capacit ance	Insulation Resistance(DF(%m ax.)	Measuri ng a conditio		Thickness	(mm) ※4	Solderir	ng method
	istics (JIS/EIA)	(μF)	M Ω · μ F)min※2		n:3	L:::4	W::4	t	Wave	Reflow
UMK212 B7104□G	X7R	0.10	THE STATE OF THE S	3.5	2	М	М	1.25±0.1	0	0
UMK212 B7224□G	X7R	0.22		3.5	2	М	М	1.25±0.1	0	0
UMK212 B7474□G	X7R	0.47		3.5	2	М	М	1.25±0.1	0	0
GMK212 B7105□G	X7R	1.0		3.5	2	М	М	1.25±0.1	0	0
TMK212 B7105□G	X7R	1.0		3.5	2	М	М	$1.25\!\pm\!0.1$	0	0
EMK212 B7474 D	X7R	0.47		3.5	2	М	М	0.85±0.1	0	0
EMK212 B7105□D	X7R	1.0	100	5.0	2	М	М	0.85±0.1	×	0
EMK212 B7225□D	X7R	2.2	100	5.0	2	Q	Q	$0.85 \!\pm\! 0.1$	×	0
EMK212 B7105□G	X7R	1.0		3.5	2	М	М	1.25±0.1	0	0
EMK212 B7225□G	X7R	2.2	100	10.0	2	М	М	$1.25\!\pm\!0.1$	×	0
EMK212 B7475□G	X7R	4.7	100	10.0	2	М	М	1.25±0.1	×	0
LMK212 B7105□D	X7R	1.0		3.5	2	М	М	$0.85\!\pm\!0.1$	×	0
LMK212 B7225□D	X7R	2.2	100	5.0	2	Q	Q	0.85±0.1	×	0
LMK212 B7105□G	X7R	1.0		3.5	2	М	М	1.25±0.1	0	0
LMK212 B7225□G	X7R	2.2		5.0	2	М	М	1.25±0.1	×	0
LMK212 B7475□G	X7R	4.7	100	10.0	2	М	М	1.25±0.1	×	0
JMK212 B7106□G	X7R	10.0	100	10.0	3	Q	Q	$1.25\!\pm\!0.15$	×	0

[Note] %1: \square is for Tolerance code K or M.

 $\mbox{\em \dot{x}}$ 2 : Blank indicates 500M $\mbox{\em Ω}$ • $\mbox{\em μ}$ F min.

%3 : Per P4

%4 : Per Table3

Table 2 Specification for Capacitance Change and Dissipation Factor Change

	Resistar Soldering /The Shoo	g Heat rmal ck	(St	Humidity eady stat				iture Loa			dity Load	
Ordering code	Capaci tance change rate(%)	DF (%m ax.)	Capaci tance change rate(%)	DF (%ma x.)	IR after test (MΩ+ μF min.) ※1	Capaci tance change rate(%)	DF (%ma x.)	Applie d voltag e (%)	IR after test (MΩ· μF min.) ¾1	Capaci tance change rate(%)	DF (%ma x.)	IR after test (M Ω · μ F min.) ×2
UMK212 BJ104□G	±7.5	3.5	±12.5	5.0		±12.5	5.0			±12.5	5.0	
UMK212 BJ224□G	±7.5	3.5	±12.5	5.0		±12.5	5.0	150		±12.5	5.0	
UMK212 BJ474□G	±7.5	3.5	±12.5	5.0		±12.5	5.0	150		±12.5	5.0	
UMK212 BJ105□G	±7.5	5.0	±12.5	7.5		±12.5	7.5	150		±12.5	7.5	
TMK212 BJ474□D	±7.5	3.5	±12.5	7.5		±12.5	7.5			±15.0	7.5	
TMK212 BJ105□D	±7.5	5.0	±12.5	7.5		±12.5	7.5			±15.0	7.5	
TMK212 BJ225□D	±7.5	5.0	±12.5	7.5		±20.0	7.5	150		±20.0	7.5	
TMK212 BJ475□D-TD	±7.5	10.0	±12.5	20.0	10	±20.0	20.0	150	10	±20.0	20.0	5
TMK212 BJ225□G	±7.5	5.0	±12.5	7.5		±12.5	7.5	150		±12.5	7.5	
TMK212 BJ475□G	±7.5	10.0	±12.5	20.0	10	±20.0	20.0	150	10	±20.0	20.0	5
EMK212 BJ105□D	±7.5	5.0	±12.5	7.5		±12.5	7.5			±12.5	7.5	
EMK212 BJ225□D	±7.5	5.0	±12.5	7.5		±20.0	7.5			±20.0	7.5	
EMK212 BJ475□D	±7.5	10.0	±12.5	20.0	10	±20.0	20.0	150	10	±20.0	20.0	5
EMK212 BJ106□D-TD	±15.0	10.0	±30.0	20.0	10	±30.0	20.0	150	10	±30.0	20.0	5
EMK212 BJ225□G	±7.5	5.0	±12.5	7.5		±12.5	7.5			±12.5	7.5	
EMK212 BJ475□G	±7.5	5.0	±12.5	7.5		±20.0	7.5	150		±20.0	7.5	
EMK212 BJ106□G	±7.5	10.0	±12.5	20.0	10	±20.0	20.0	150	10	±20.0	20.0	5
LMK212 BJ475□K	±15.0	10.0	±30.0	20.0	10	±30.0	20.0	150	10	±30.0	20.0	5
LMK212 BJ105□D	±7.5	3.5	±12.5	5.0		±12.5	5.0			±12.5	5.0	
LMK212 BJ225□D	±7.5	5.0	±12.5	7.5		±12.5	7.5			±12.5	7.5	
LMK212 BJ475□D	±7.5	10.0	±12.5	20.0	10	±20.0	20.0		10	±20.0	20.0	5
LMK212 BJ106□D	±15.0	10.0	±30.0	20.0	10	±30.0	20.0	150	10	±30.0	20.0	5
LMK212 BJ225□G	±7.5	5.0	±12.5	7.5		±12.5	7.5			±12.5	7.5	
LMK212 BJ475□G	±7.5	5.0	±12.5	7.5		±12.5	7.5			±12.5	7.5	
LMK212 BJ106□G	±7.5	10.0	±12.5	20.0	10	±20.0	20.0		10	±20.0	20.0	5
LMK212 BJ226MG	±15.0	10.0	±30.0	20.0	10	±30.0	20.0	150	10	±30.0	20.0	5
JMK212 BJ475□K	±15.0	10.0	±30.0	20.0	10	±30.0	20.0	150	10	±30.0	20.0	5
JMK212 BJ106MK	±15.0	10.0	±25.0	15.0	10	±25.0	15.0	150	10	±25.0	15.0	5
JMK212 BJ475□D	±7.5	10.0	±12.5	20.0	10	±20.0	20.0		10	±20.0	20.0	5
JMK212 BJ106□D	±15.0	10.0	±30.0	20.0	10	±30.0	20.0		10	±30.0	20.0	5
JMK212 BJ226MD	±15.0	10.0	±25.0	15.0	10	±25.0	15.0	150	10	±25.0	15.0	5
JMK212 BJ475□G	±7.5	5.0	±12.5	7.5		±12.5	7.5			±12.5	7.5	
JMK212 BJ106□G	±7.5	10.0	±12.5	20.0	10	±20.0	20.0		10	±20.0	20.0	5
JMK212 BJ226MG	±15.0	10.0	±30.0	20.0	10	±30.0	20.0	150	10	±30.0	20.0	5
JMK212 BJ476MG	±15.0	10.0	±25.0	15.0	10	±25.0	15.0	150	10	±25.0	15.0	5

[Note] %1 : Blank indicates lesser value of 50M Ω • μ F min.

 $\mbox{\%2}$: Blank indicates lesser value of 25M Ω • μ F min.

 $\frak{3}:$ Blank indicates rated voltage 200%

 Table 2
 Specification for Capacitance Change and Dissipation Factor Change

	Resista Solderin /The Sho	ig Heat irmal		Humidity (Steady state) High Temperature Loading				Humidity Loading				
Ordering code	Capaci tance change rate(%)	DF (%ma x.)	Capaci tance change rate(%)	DF (%ma x.)	IR after test (M Ω· μF min.) ※1	Capaci tance change rate(%)	DF (%ma x.)	Applie d voltag e (%) 33	IR after test (M Ω· μF min.) **1	Capaci tance change rate(%)	DF (%ma x.)	IR after test (M Ω· μF min.) **2
UMK212 F224ZD	±20.0	7.0	±30.0	11.0		±30.0	11.0			±30.0	11.0	
UMK212 F474ZG	±20.0	7.0	±30.0	11.0		±30.0	11.0			±30.0	11.0	
UMK212 F105ZG	± 20.0	7.0	±30.0	11.0		± 30.0	11.0			±30.0	11.0	
EMK212 F225ZG	±20.0	7.0	\pm 30.0	11.0		±30.0	11.0			±30.0	11.0	
LMK212 F225ZD	±20.0	9.0	±30.0	11.0		\pm 30.0	11.0			±30.0	11.0	
LMK212 F475ZG	±20.0	9.0	±30.0	11.0		\pm 30.0	11.0			±30.0	11.0	
LMK212 F106ZG	±20.0	16.0	\pm 30.0	19.5		± 30.0	19.5			±30.0	19.5	
JMK212 F475ZD	±20.0	16.0	±30.0	19.5		±30.0	19.5			±30.0	19.5	
JMK212 F106ZG	± 20.0	16.0	±30.0	19.5		± 30.0	19.5			±30.0	19.5	


	Resista Solderin /The	ig Heat irmal		lumidity ady state	9)	High Temperature Loading			ling	Humidity Loading		
Ordering code	Capaci tance change rate(%)	DF (%ma x.)	Capaci tance change rate(%)	DF (%ma x.)	IR after test (M Ω· μF min.) **1	Capaci tance change rate(%)	DF (%ma x.)	Applie d voltag e (%) 33	IR after test (M Ω· μF min.) ※1	Capaci tance change rate(%)	DF (%ma x.)	IR after test (M Ω· μF min.) **2
UMK212 B7104□G	±7.5	3.5	±12.5	5.0		±12.5	5.0			±12.5	5.0	
UMK212 B7224□G	±7.5	3.5	±12.5	5.0		\pm 12.5	5.0	150		\pm 12.5	5.0	
UMK212 B7474□G	±7.5	3.5	±12.5	5.0		\pm 12.5	5.0	150		\pm 12.5	5.0	
GMK212 B7105□G	±7.5	3.5	±12.5	7.5		±12.5	7.5	150		±12.5	7.5	
TMK212 B7105□G	±7.5	3.5	±12.5	7.5		\pm 12.5	7.5	150		±12.5	7.5	
EMK212 B7474□D	±7.5	3.5	±12.5	5.0		±12.5	5.0			±12.5	5.0	
EMK212 B7105□D	±7.5	5.0	\pm 12.5	7.5		\pm 12.5	7.5			± 15.0	7.5	
EMK212 B7225□D	±7.5	5.0	±12.5	7.5		± 20.0	7.5	150		±20.0	7.5	
EMK212 B7105□G	±7.5	3.5	\pm 12.5	5.0		\pm 12.5	5.0			\pm 12.5	5.0	
EMK212 B7225□G	±7.5	10.0	\pm 12.5	20.0	10	± 25.0	20.0	150	10	± 25.0	20.0	5
EMK212 B7475□G	±7.5	10.0	±12.5	20.0	10	± 20.0	20.0	150	10	±20.0	20.0	5
LMK212 B7105□D	±7.5	3.5	±12.5	5.0		±12.5	5.0			±12.5	5.0	
LMK212 B7225□D	±7.5	5.0	±12.5	7.5		±20.0	7.5			±20.0	7.5	
LMK212 B7105□G	±7.5	3.5	±12.5	5.0		±12.5	5.0			±12.5	5.0	
LMK212 B7225□G	±7.5	5.0	±12.5	7.5		±12.5	7.5			±12.5	7.5	
LMK212 B7475□G	±7.5	10.0	±12.5	20.0	10	±20.0	20.0	150	10	±20.0	20.0	5
JMK212 B7106□G	±7.5	10.0	±12.5	20.0	10	±20.0	20.0	150	10	±20.0	20.0	5

[Note] %1 : Blank indicates lesser value of 50M Ω • μ F min.

 $\mbox{\%2}$: Blank indicates lesser value of 25M Ω • μ F min.

 $\frak{3}$: Blank indicates rated voltage 200%

Fig.1 Shape and Dimensions



Ni Based Electrodes[Class II]


No.	Name	Material
1	Terminal Electrodes (Surface)	Sn Plating
2	Terminal Electrodes	Ni Plating
	Terrilliai Liectiodes	Cu Plating
3	External Electrodes	Ni
4	Internal Electrodes	Ni
5	Dielectric	Barium titanate

Table 3

		L		W	t	е
Туре	Toler ance code	Dimensions	Toler ance code	Dimensions	Dimensions	Dimensions
	М	2.0±0.1	М	1.25±0.1		
212	Ø	2.0 ± 0.15	Ŋ	1.25 ± 0.15	Per Table1	0.5 ± 0.25
	R	2.0 ± 0.2	R	1.25 ± 0.2		

[Unit: mm]


Fig.2 Board / Test Jig of Adhesive Force of Terminal Electrodes, Vibration and Thermal Shock



 Size (L×W)
 a
 b
 c

 2.0×1.25
 1.2
 4.0
 1.65

[Unit: mm]



Cross Section

Material: Glass epoxy board [JIS C 6484]


Copper foil (Thickness: 0.035mm)

Solder resist

Remarks: Uniform soldering shall be conducted with solder (H60A or H63A in JIS Z 3282) by using an iron or soldering oven.

Soldering shall be conducted with care of avoiding abnormality such as heat shock.

Fig.3 Test Board




Material: Glass epoxy board [JIS C 6484]

Copper foil (Thickness: 0.035mm)

Solder resist

Size (L×W)	а	b	С
2.0×1.25	1.2	4.0	1.65


[Unit: mm]



Apply pressure at the rate of 0.5mm/sec. until amount of deflection reaches 1.0mm.

Tape Packaging107 · 212 · 316 · 325Type

⊚In case of taping packing, paper tapes shall be used for 107 type product and product with 0.85mm thickness, plastic tapes shall be used for product with thickness rank of 1.15mm, 1.25mm, 1.5mm, 1.6mm, 1.9mm, 2.5mm and 325 Type with 0.85mm rank thickness.



<u>Dimensions</u> *

Туре	Α	В
107	1.0±0.2	1.8±0.2
107	1.1±0.2 ※ ※	1.9±0.2 ※ ※
212	1.65±0.2	2.4±0.2
316	2.0±0.2	3.6±0.2
325	2.8±0.2	3.6±0.2

[Unit: mm]


Dimensions

Type	С	D	E	F	G	H	J	кж	t ※
107~ 325	8.0±0.3	3.5±0.05	1.75±0.1	4.0±0.1	2.0±0.05	4.0±0.1	φ 1.5 +0.1/-0	(Paper tape)	1.1 max (Paper tape) 1.2 max (Paper tape) ***

 $\divideontimes A,\,B,K,\,t:\,Sufficient\,clearance.$

[Unit: mm]

** LMK107BJ475MKLTD,LMK107BJ106MALTD,AMK107BJ226MA-T



Dimensions of Reel [Unit: mm]

Туре	А	В	С	D	E	W	t	R
107~325	ϕ 178 \pm 2.0	φ 50 min	ϕ 13.0 \pm .0.2	ϕ 21.0 \pm 0.8	2.0±0.5	10.0±1.5	2.5max.	1.0

Tape Packaging107,212,316,325TYPE

- 1. Taping shall be right-sided wound. When the end is pulled out, sprocket hole will be at the right-hand side.
- 2. The "t" dimension axis and "W" dimension axis of the following components inserted in chip cavity shall be randomly perpendicular to tape face.

107(0603) type with 0.8mm rank thickness, 212(0805) type with 1.25mm rank thickness,

316(1206) type with 1.6mm rank thickness, 325(1210) type with 2.5mm rank thickness

- 3. For packaging chips by taping, blank spaces are provided on taping as shown in the figure.
 - Leader part


400mm min.

· Leader part (Blank part)


100mm min.

Trailer (Blank part)

160mm min.



- 4. Top tape, bottom tape of paper taping and the seal tape of plastic taping shall not be crossed over sprocket holes.
- 5. There shall no seam on paper tape and plastic tape.
- 6. Tensile strength of the tape shall be 5N(0.51kgf) or over.
- 7. Number of the chip missing at Chip packaging area shall be 1 piece maximum per reel.
- 8.Standard number of chips contained in a reel shall be per Table shown below.
- 9. Label indicating part No., quantity and control No. shall be attached to the outside of reel.
- 10. Peeling strength of seal tape (or top tape) shall be $0.1\sim0.7N$ ($10.2\sim71.4gf$) when seal tape (or top tape) is peeled from carrier tape at an angle of $0^{\circ} \sim 20^{\circ}$




Quantity of taping package

Туре	Thickness (rank)	Quantity	Carrier
i ype	Unit: mm	(pcs/reel)	tape
107	0.45(K)		
107	0.80(A)	4,000	paper
	0.45(K)	4,000	paper
212	0.85(D)		
	1.25(G)	3,000	plastic
	0.85(D)	4,000	paper
316	1.15(F)	3,000	
310	1.25(G)	3,000	plastic
	1.60(L)	2,000	

Туре	Thickness rank	Quantity	Carrier	
ı ype	Unit: mm	(pcs/reel)	tape	
	0.85(D)			
325	1.15(F)		plactic	
	1.50(H)	2,000		
	1.90(N)		plastic	
	1.9+0.1/-0.2(Y)			
	2.50(M)※	500or1000		

**For 325 type/2.50(M) thickness products, "-T" means 500 pcs per reel and "-P"means 1000 pcs per reel.

Tape Packaging107,212,316,325TYPE



Customer Label contents

- 1. Manufacturer Name
- 2. Customer Parts No.
- 3. Our parts no.
- 4. Quantity
- 5. Control No.

(Shipping lot number) 💥

6. Manufacturing site

MADE IN OOO

We control our products by control number, and shipping lot numbering is not marked on customer label. Shipping lot number is marked on our control label. Shipping lot number is traceable from our control number marked on customer label

[107,212,316,325]

Code	Α	A B C Ree			el
Size 190 1	185	70	5 reels	max.	
Size	190	100	140	10 reels	max.

Material: Paper


[Unit: mm]

(The size is only for reference.)

Packaging unit: Maximum 5 reels or 10 reels in a box

• To attach labels means that all products are passed.


Shipping Lot No.



- ①First digit of manufactured year Example: $201\underline{0}$ year \rightarrow 0
- ②Manufactured month and its symbol are described in below table.
- ③Sequential number is consist of alphabet, numeric and space.


Month	1	2	3	4	5	6	7	8	9	10	11	12
code	Α	В	С	D	E	F	G	Н	J	K	L	М

Recommended Soldering Profiles for Lead-free Solder Paste



% Ceramic chip components should be preheated to within 100 to 130°C from the soldering, temperature.


XAssured to be reflow soldering for 2 times.



*Ceramic chip components should be preheated to within 100 to 130°C from the soldering, temperature.

XAssured to be wave soldering for 1 time.

*Except for reflow soldering type.



※ △T ≤ 150°C (3216Type max), △T ≤ 130°C (3225Type min)

※Preheating control: Boards and components should be preheated sufficiently with temperature over 150°C, and soldering should be conducted by soldering iron while temperature of boards and components keep sufficient temperature.

XThe soldering iron should not directly touch the components.

*Assured to be soldering iron for 1 time.

 \times It is recommended to use 20W soldering iron and the tip is 1 ϕ or less.

Temperature in usage of Pb-free solder (Sn-3Ag-0.5Cu)

Case size	Soldering iron tip temp.	Preheating temp.
3216 type	≦350°C	≧150°C
3225 type i	≦280°C	≧150°C

Note: The above profiles are the maximum allowable soldering condition, therefore these profiles are not always recommended.

Operating conditions for guarantee of this product are as shown in the specification.

Please note that Taiyo Yuden Co., Ltd. shall not be responsible for a failure and/or abnormality which are caused by use under the conditions other than aforesaid operating conditions.

■ All electronic components listed in this specification are developed, designed and intended for use in general electronics equipment.(for AV, office automation, household, office supply, information service, telecommunications, (such as mobile phone or PC) etc.). Before incorporating the components or devices into any equipment in the field such as transportation, (automotive control, train control, ship control), transportation signal, disaster prevention, medical, public information network(telephone exchange, base station) etc. which may have direct influence to harm or injure a human body, please contact Taiyo Yuden Co., Ltd. for more detail in advance.

Do not incorporate the products into any equipment in fields such as aerospace, aviation, nuclear control, submarine system, military, etc. where higher safety and reliability are especially required. In addition, even electronic components or functional modules that are used for the general electronic equipment, if the equipment or the electric circuit require high safety or reliability function or performances, a sufficient reliability evaluation check for safety shall be performed before commercial shipment and moreover, due consideration to install a protective circuit is strongly recommended at customer's design stage.

- Please conduct validation and verification of products in actual condition of mounting and operating environment before commercial shipment of the equipment.
- The contents of this specification are applicable to the products which are purchased from our sales offices or distributors (so called TAIYO YUDEN's official sales channel).

It is only applicable to the products purchased from any of TAIYO YUDEN's official sales channel.

- Please note that Taiyo Yuden Co., Ltd. shall have no responsibility for any controversies or disputes that may occur in connection with a third party's intellectual property rights and other related rights arising from your usage of products in this specification. Taiyo Yuden Co., Ltd. grants no license for such rights.
- Caution for export

Certain items in this specification may require specific procedures for export according to Foreign Exchange and Foreign Trade Control Law of Japan, U.S. Export Administration Regulations, and other applicable regulations. Should you have any question or inquiry on this matter, please contact our sales staff.