Document No.

Specifications Date: 28.JUN.2010

Multilayer Ceramic Chip Capacitor NICKEL BASED ELECTRODES

MLCEE100P3

Item

Multilayer Ceramic Capacitor Class II

(CC1206)

1. Scope

This specification covers multilayer chip type ceramic capacitor (Pb-Free) for use (for reflow soldering) in electronic appliances and electric communication equipment.

2. Part Numbering System

Voltage

25V

Part number is indicated as follows:

Ni based electrodes: $\underline{\begin{array}{ccc} T \\ \hline 1 \end{array}}$ MK $\underline{\begin{array}{ccc} 316 \\ \hline 2 \end{array}}$

① Rated voltage

Code

Τ

(2)	Size	(mm)

	© 0.20 ()				
Code		Size			
	316	3.2×1.6			

4 Tolerance

Code	Tolerance			
K	±10%			
М	±20%			

6 Packaging

Packaging	Code
Taping	T

③ Temperature Characteristic

Class II Capacitance change rate		Temperature range	Reference temperature
BJ (X5R) ±15%(EIA)		-55∼+85℃	25℃

⑤ Thickness code (Ni based electrodes)

Туре	Thickness rank (mm)	Code
316	1.60	L

Multilayer Ceramic Chip Capacitor

3. Test Conditions

Standard test conditions shall be temperature of 5 to 35° C, relative humidity of 45 to 85% and air pressure of 86 to 106kPa. Test shall be conducted at temperature of $25\pm3^{\circ}$ C, relative humidity of 60 to 70% and air pressure of 86 to 106kPa if test result is suspectable.

Unless otherwise specified, all tests shall be conducted under standard test conditions.

4. Construction, Dimensions and Performance

Details of construction, dimensions and performance shall be specified in the following pages.

5. Packaging

Packaging shall be made to avoid damages of capacitors during transportation or storage. And it shall be marked with part number, quantity, lot number and manufacturer's name on its appropriate position.

6. Manufacturing site

TAIYO YUDEN CO., LTD. (JAPAN)
TAIYO YUDEN (SARAWAK) SDN, BHD. (MALAYSIA)
KOREA KYONG NAM TAIYO YUDEN CO., LTD. (KOREA)
TAIYO YUDEN (GUANG DONG) CO., LTD. (CHINA)
TAIYO YUDEN (PHILIPPINES) INC. (PHILIPPINES)

7. Precautions

•Please refer to precautions in our general catalog prior to product usage.

If you need further information, please contact us.

·CAUTION: Contents of this specification cannot be assured with Sn-Zn lead-free solder usage.

8. Storage conditions

- To maintain the solderability of terminal electrodes and to keep the packaging material in good condition, care must be taken to control temperature and humidity in the storage area. Humidity should especially be kept as low as possible.
- · Recommended conditions

Ambient temperature: 30℃ and below

Humidity: 70% RH and below

The ambient temperature must be kept below 40° C. Even under ideal storage conditions, capacitor electrode solderability decreases with time. Therefore ceramic chip capacitors should be used within 6 months from the time of delivery. If exceeding the above period, please check solderability before using the capacitors.

The packaging material should be kept where no chlorine or sulfur exists in the air.

Multilayer Ceramic Chip Capacitor
9. RoHS compliance
This product conform to RoHS.
 "RoHS compliance" means that the product does not contain lead, cadmium, mercury,
hexavalent chromium, PBB or PBDE referring to EU Directive 2002/95/EC, except other non-restricted
substances or impurities which cannot be technically removed at refining process.
,


No.	Item	Specified Value	Remarks
1	Operating Temperature Range	Capable of continuous operation under these conditions.	-55~+85℃
2	Shape and Dimensions	Per Fig.1	
3	Heat Treatment		Initial value shall be measured after test sample is heat-treated at 150 +0/-10 $^{\circ}$ C for an hour and kept at room temperature for 24 \pm 2hours.
4	Voltage Treatment		Initial value shall be measured after test sample is voltage-treated for an hour at temperature and voltage which are specified as test conditions, and kept at room temperature for 24±2hours.
5	Dielectric Withstanding Voltage (between terminals)	No abnormality	Conforming to EIA RS-198-D (1991). 250% of DC rated voltage shall be applied for 1 to 5 seconds. Charging and discharging current shall be 50mA or less.
6	Insulation Resistance	100M Ω · μ F min.	Conforming to EIA RS-198-D (1991). Voltage for the measurement shall be rated voltage and voltage applying time shall be 1 minute ± 5 seconds. Charging and discharging current shall be 50mA or less.
7	Capacitance and Tolerance	10.0 μ F Κ (±10%) Μ (±20%)	Conforming to EIA RS-198-D (1991). Heat treatment specified in No.3 of the specification shall be conducted prior to measurement. Measuring frequency and voltage shall conform to the table shown below. Measuring Measuring Frequency Voltage 1kHz±10% 1.0±0.2Vrms
8	Dissipation Factor (DF)	5.0%max	Conforming to EIA RS-198-D (1991). Heat treatment specified in No.3 of the specification shall be conducted prior to measurement. Measuring frequency and voltage shall conform to the table shown below. Measuring Measuring Frequency Voltage 1kHz±10% 1.0±0.2Vrms

No.	Item	Specified Value	Remarks
9	Temperature Characteristic	Per P1③Temperature Characteristic	Conforming to EIA RS-198-D (1991). Heat treatment specified in No.3 of the specification shall be conducted prior to measurement. Maximum capacitance deviation in both (+) and (-) sides in range of lowest temperature to highest temperature for capacitor shall be indicated in ratio of variation in reference to capacitance value at reference temperature.
10	Adhesive Force of Terminal Electrodes	Terminal electrodes shall be no exfoliation or a sign of exfoliation.	Test sample shall be soldered to test board shown in Fig.2 and a force of 5N{0.51kgf} shall be applied in arrow direction for 30 ± 5 seconds.
11	Vibration	Initial performance shall be satisfied.	Conforming to EIA RS-198-D (1991). Test sample shall be soldered to board shown in Fig.2. Heat treatment specified in No.3 of the specification shall be conducted prior to test. Test conditions: Frequency range: 10~55Hz Overall amplitude: 1.5mm Sweeping method: 10~55~10Hz for 1 min. Each two hours in X,Y,Z direction: 6 hours in total

No.		tem	Specified Value	Remarks
12	Resistance to Soldering Heat	Appearance Capacitance Change Dissipation Factor Insulation Resistance	No abnormality Within ±7.5% Initial value shall be satisfied. Initial value shall be satisfied.	Conforming to EIA RS-198-D (1991). Test sample shall be completely submerged in molten solder of 270±5°C for 3±0.5 seconds. Preheating as shown in the table below shall be continuously conducted before submersion and test sample shall be kept at normal temperature after test. Sequence Temperature (°C) (min)
		Dielectric Withstanding Voltage (between terminals)	No abnormality	$\begin{array}{ c c c c c }\hline 1 & 80{\sim}100 & 5{\sim}10 \\\hline 2 & 150{\sim}200 & 5{\sim}10 \\\hline \end{array}$ Heat treatment specified in No.3 of the specification shall be conducted prior to test. Measurement shall be conducted after test sample is kept at room temperature for 24 \pm 2 hours.
13	Solderability		More than 95% of terminal electrode shall be covered with fresh solder.	[Eutectic] Used solder shall be [JIS Z 3282 H60A or H63A]. Test sample shall be completely submerged in molten solder of 230±5°C for 4±1 seconds. [Pb free] Used solder shall be [Sn/3.0Ag/0.5Cu]. Test sample shall be completely submerged in molten solder of 245±3°C for 4±1 seconds.
14	Thermal Shock	Appearance Capacitance Change Dissipation Factor	No abnormality Within $\pm 7.5\%$ Initial value shall be satisfied.	Conforming to EIA RS-198-D (1991). Test sample shall be soldered to board shown in Fig.2. Heat treatment specified in No.3 of the specification shall be conducted prior to test. Test sample shall be kept for specified time at each of temperature in steps 1 to 4 shown below in sequence.
		Insulation Resistance Dielectric Withstanding Voltage (between terminals)	Initial value shall be satisfied. No abnormality	
	<u>,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,</u>			method, and measurement shall be conducted after test sample is kept for 24 ± 2 hours.

No.	lte	em	Specified Value	Remarks
15	Humidity (Steady	Appearance	No abnormality	Conforming to EIA RS-198-D (1991). Test sample shall be at $40 \pm 2 ^{\circ}\!$
	State)	Capacitance Change	Within±12.5%	humidity of 90 to 95% for 500 +24/-0 hours. Heat treatment specified in No.3 of the specification
	:	Dissipation Factor	7.5%max	shall be conducted prior to test. Measurement shall be conducted after test sample is
		Insulation Resistance	50M Ω • μ F min.	kept for 24±2 hours.
16	High Temperature	Appearance	No abnormality	Conforming to EIA RS-198-D (1991). Test sample shall be put in thermostatic oven with
	Loading	Capacitance Change	Within±20.0%	maximum temperature and 150% of DC rated voltage shall be continuously applied for 1000 +48/-0
		Dissipation Factor	7.5%max	hours Charging and discharging current shall be 50mA or
		Insulation Resistance	50MΩ • μ F min.	less. Voltage treatment specified in No.4 of the specification shall be conducted prior to test. Measurement shall be conducted after test sample is kept for 24±2 hours.
17	Humidity Loading	Appearance	No abnormality	Conforming to EIA RS-198-D (1991). Test sample shall be put in thermostatic oven with 40
		Capacitance Change	Within±20.0%	$\pm 2^{\circ}$ C and relative humidity 90 to 95% and DC rated voltage shall be continuously applied for 500 +24/-0
		Dissipation Factor	7.5%max	hours. Charging and discharging current shall be 50mA or
		Insulation Resistance	25M Ω · μ F min.	less. Voltage treatment specified in No.4 of the specification shall be conducted prior to test. Measurement shall be conducted after test sample is kept for 24±2 hours.
18	Bending Strength	Appearance	No abnormality	Test sample shall be soldered to test board as shown in Fig.3.
	J	Capacitance Change	Within±12.5%	Soldering shall be conducted with care of avoiding an abnormality such as heat shock. Deflection test is such that force to cause deflection as much as 1.0mm is applied for 10 seconds method shown in Fig.4. Measurement shall be conducted with deflection 1.0mm.

Fig.1 Shape and Dimensions




Ni Based Electrodes[Class ${\mathbb I}$]

No.	Name	Material
1	Terminal Electrodes (Surface)	Sn Plating
2	Terminal Electrodes	Ni Plating
	reminal Electrodes	Cu Plating
3	External Electrodes	Ni
4	Internal Electrodes	Ni
5	Dielectric	Barium titanate

		L		W	t	е
Туре	Toler ance code	Dimensions	Toler ance code	Dimensions	Dimensions	Dimensions
316	Q	3.2±0.15	Q	1.6±0.15	1.6±0.2	0.5+0.35/-0.25

[Unit: mm]

Fig.2 Board / Test Jig of Adhesive Force of Terminal Electrodes, Vibration and Thermal Shock



 Size (L×W)
 a
 b
 c

 3.2×1.6
 2.2
 5.0
 2.0

 [Unit: mm]

 Scratch tool

Material: Glass epoxy board [JIS C 6484]

Copper foil (Thickness: 0.035mm)


Solder resist

Remarks: Uniform soldering shall be conducted with solder (H60A or H63A in JIS Z 3282) by using an iron or soldering oven.

Soldering shall be conducted with care of avoiding abnormality such as heat shock.

Fig.4

Fig.3 Test Board



Material: Glass epoxy board [JIS C 6484]

Copper foil (Thickness: 0.035mm)

Solder resist

Applied 10	
- I R230 I I - 1 - 1 - 1 - 1 - 1 - 1 - 1 - 1 - 1	mount of
Board \/ I . IZ	eflection
	-3
	<u> </u>
	I
← → ← → → → → → → → → → →	
,	[Unit: mm]

Cross Section


Apply pressure at the rate of 0.5mm/sec. until amount of deflection reaches 1.0mm.

Size (L×W)	а	b	С
3.2×1.6	2.2	5.0	2.0

[Unit: mm]

Tape Packaging107 · 212 · 316 · 325Type

◎In case of taping packing, paper tapes shall be used for 107 type product and product with 0.85mm thickness, plastic tapes shall be used for product with thickness rank of 1.15mm, 1.25mm, 1.5mm, 1.6mm, 1.9mm, 2.5mm and 325 Type with 0.85mm rank thickness.



Dimensions X

Type	Α	В		
107	1.0±0.2	1.8±0.2		
107	1.1±0.2※※	1.9±0.2%%		
212	1.65±0.2	2.4±0.2		
316	2.0 ± 0.2	3.6±0.2		
325	2.8±0.2	3.6±0.2		

[Unit: mm]


Dimensions

Туре	С	D	E	F	G	Н	J	K%	t*
107~ 325	8.0±0.3	3.5±0.05	1.75±0.1	4.0±0.1	2.0±0.05	4.0±0.1	φ 1.5 +0.1/-0	(Paper tape)	1.1 max (Paper tape) 1.2 max (Paper tape) ***

※A, B,K, t : Sufficient clearance.

[Unit: mm]

** XLMK107BJ475MKLTD,LMK107BJ106MALTD,AMK107BJ226MA-T



Dimensions of Reel [Unit: mm]

Туре	Α	В	С	D	E	W	t	R
107~325	φ178±2.0	ϕ 50 min	ϕ 13.0 \pm .0.2	ϕ 21.0 \pm 0.8	2.0±0.5	10.0±1.5	2.5max.	1.0

Tape Packaging107,212,316,325TYPE

- 1. Taping shall be right-sided wound. When the end is pulled out, sprocket hole will be at the right-hand side.
- 2. The "t" dimension axis and "W" dimension axis of the following components inserted in chip cavity shall be randomly perpendicular to tape face.

107(0603) type with 0.8mm rank thickness, 212(0805) type with 1.25mm rank thickness,

316(1206) type with 1.6mm rank thickness, 325(1210) type with 2.5mm rank thickness

- 3. For packaging chips by taping, blank spaces are provided on taping as shown in the figure.
 - · Leader part


400mm min.

· Leader part (Blank part)


100mm min.

· Trailer (Blank part)

160mm min.



- 4. Top tape, bottom tape of paper taping and the seal tape of plastic taping shall not be crossed over sprocket holes.
- 5. There shall no seam on paper tape and plastic tape.
- 6. Tensile strength of the tape shall be 5N(0.51kgf) or over.
- 7. Number of the chip missing at Chip packaging area shall be 1 piece maximum per reel.
- 8.Standard number of chips contained in a reel shall be per Table shown below.
- 9. Label indicating part No., quantity and control No. shall be attached to the outside of reel.
- 10. Peeling strength of seal tape (or top tape) shall be $0.1\sim0.7N$ ($10.2\sim71.4gf$) when seal tape (or top tape) is peeled from carrier tape at an angle of $0^{\circ} \sim 20^{\circ}$




Quantity of taping package

	Qualiti	if or taping paorago				
Туре		Thickness (rank)	Quantity	Carrier		
	Type	Unit: mm	(pcs/reel)	tape		
	107	0.45(K)				
	107	0.80(A)	4,000	nanar		
	212	0.45(K)	4,000	paper		
		0.85(D)				
		1.25(G)	3,000	plastic		
		0.85(D)	4,000	paper		
	316	1.15(F)	3,000			
		1.25(G)	3,000	plastic		
		1.60/1.)	2 000			

Туре	Thickness rank	Quantity	Carrier	
Type	Unit: mm	(pcs/reel)	tape	
	0.85(D)			
	1.15(F)			
205	1.50(H)	2,000		
325	1.90(N)		plastic	
	1.9+0.1/-0.2(Y)			
	2.50(M)※	500or1000		

Tape Packaging 107, 212, 316, 325 TYPE



Customer Label contents

- 1. Manufacturer Name
- 2. Customer Parts No.
- 3. Our parts no.
- 4. Quantity
- 5. Control No.(Shipping lot number) ※
- 6. Manufacturing site MADE IN OOO

We control our products by control number, and shipping lot numbering is not marked on customer label. Shipping lot number is marked on our control label. Shipping lot number is traceable from our control number marked on customer label

[107,212,316,325]

Code	Α	В	С	Ree	əl
Size	190	185	70	5 reels	max.
		100	140	10 reels	max.

Material: Paper


[Unit: mm]

(The size is only for reference.)

Packaging unit: Maximum 5 reels or 10 reels in a box

· To attach labels means that all products are passed.


Shipping Lot No.



- ①First digit of manufactured year
- Example: $201\underline{0}$ year \rightarrow 0
- ②Manufactured month and its symbol are described in below table.
- ③Sequential number is consist of alphabet, numeric and space.


Month	1	2	3	4	5	6	7	8	9	10	11	12
code	Α	В	С	D	Е	F	G	Н	J	K	L	М

Recommended Soldering Profiles for Lead-free Solder Paste



«Ceramic chip components should be preheated to within 100 to 130°C from the soldering, temperature.


*Assured to be reflow soldering for 2 times.



**Ceramic chip components should be preheated to within 100 to 130°C from the soldering, temperature.

*Assured to be wave soldering for 1 time.

XExcept for reflow soldering type.



※ △T ≤ 150°C (3216Type max), △T ≤ 130°C (3225Type min)

※Preheating control: Boards and components should be preheated sufficiently with temperature over 150°C, and soldering should be conducted by soldering iron while temperature of boards and components keep sufficient temperature.

 $\ensuremath{\mbox{\ensuremath{\mbox{χ}}}\xspace}$ The soldering iron should not directly touch the components.

*Assured to be soldering iron for 1 time.

imesIt is recommended to use 20W soldering iron and the tip is 1 ϕ or less.

Temperature in usage of Pb-free solder (Sn-3Ag-0.5Cu)

Case size	Soldering iron tip temp.	Preheating temp.
3216 type	≦350°C	≧150°C
3225 type	≦280°C	≧150°C

Note: The above profiles are the maximum allowable soldering condition, therefore these profiles are not always recommended.

Operating conditions for guarantee of this product are as shown in the specification.

Please note that Taiyo Yuden Co., Ltd. shall not be responsible for a failure and/or abnormality which are caused by use under the conditions other than aforesaid operating conditions.

■ All electronic components listed in this specification are developed, designed and intended for use in general electronics equipment.(for AV, office automation, household, office supply, information service, telecommunications, (such as mobile phone or PC) etc.). Before incorporating the components or devices into any equipment in the field such as transportation, (automotive control, train control, ship control), transportation signal, disaster prevention, medical, public information network(telephone exchange, base station) etc. which may have direct influence to harm or injure a human body, please contact Taiyo Yuden Co., Ltd. for more detail in advance.

Do not incorporate the products into any equipment in fields such as aerospace, aviation, nuclear control, submarine system, military, etc. where higher safety and reliability are especially required. In addition, even electronic components or functional modules that are used for the general electronic equipment, if the equipment or the electric circuit require high safety or reliability function or performances, a sufficient reliability evaluation check for safety shall be performed before commercial shipment and moreover, due consideration to install a protective circuit is strongly recommended at customer's design stage.

- Please conduct validation and verification of products in actual condition of mounting and operating environment before commercial shipment of the equipment.
- The contents of this specification are applicable to the products which are purchased from our sales offices or distributors (so called TAIYO YUDEN's official sales channel).

It is only applicable to the products purchased from any of TAIYO YUDEN's official sales channel.

- Please note that Taiyo Yuden Co., Ltd. shall have no responsibility for any controversies or disputes that may occur in connection with a third party's intellectual property rights and other related rights arising from your usage of products in this specification. Taiyo Yuden Co., Ltd. grants no license for such rights.
- Caution for export

Certain items in this specification may require specific procedures for export according to Foreign Exchange and Foreign Trade Control Law of Japan, U.S. Export Administration Regulations, and other applicable regulations. Should you have any question or inquiry on this matter, please contact our sales staff.